

OXPURE® 830A-9

OxPure® 830A-9 is a virgin granular activated carbon produced from a special type of coal through a high temperature activation process under stringent quality control.

- High surface area
- High micropore, mesopore and macropore volumes
- High adsorption capacity for small and large size organic impurities
- Ideal for many liquid phase applications such as potable water and amine purification
- Meets ANSI / AWWA B-604 standard
- Certified to NSF / ANSI 61

PROPERTIES

SPECS	US Standard Sieve		Mesh (mm)	8x30 (2.36 – 0.60)	
		Oversize, +8 mesh	max	%	5
	Undersize, -30 mesh	max	%	5	
	Iodine Number	min	mg/g	900	
	Moisture (as packed)	max	%	5	
	Hardness Number (Ball-Pan)	min	-	82	
TYPICAL	Apparent Density		-	g/cm ³	0.38
	Hardness Number (Ball Pan)		-	-	88
	Total Ash Content		-	%	11

Standard packing is 20 kg (44 lb.) bags or 400 kg (880 lb.) bulk sacks.
 All test methods are ASTM procedures where applicable.

This information has been gathered from standard reference materials and/or test data that are assumed to be accurate and reliable. Oxbow Activated Carbon LLC makes no warranties or representations with respect to this product except as may be set forth in purchase and sale documentation relating to this product. Oxbow Activated Carbon LLC makes no other warranties of any kind, either expressed or implied, in connection with this product, including but not limited to any warranty of merchantability or fitness for a particular purpose or application. Buyer assumes all liability and risk that may arise from the use of this product. Oxbow Activated Carbon LLC reserves the right to modify product properties without prior notification.



EXPERIENCE OXBOW ACTIVATED CARBON'S DEDICATED CUSTOMER SUPPORT
 +1 760.630.5724 | sales@oxbowactivatedcarbon.com
 2535 Jason Court Oceanside, CA 92056 USA

www.oxbowactivatedcarbon.com